

Isonit Roof Coating

Gloss 12 , Gloss 20 und Gloss 50

Product description:

ISONIT roof paint is an acrylic based paint with a very good covering ability and good flow which gives the roof a beautiful surface. The roof paint has an excellent water-repelling ability, diffusion is open and allows water to get out of the painting which protects effectively against destruction of the weather.



Use:

Before use of ISONIT roof paint, the cleaning process with ISO A-clean is a very important part of the roof treatment – better pre-work – longer durability. The surface must be clean and dry, before starting the treatment. ISONIT roof coating must be applied with brush, paint roller, or spray. The weather must be stable; there must not be any warning of rain or shower.

In sunshine the ISONIT is also very suitable. It is possible to dilute with 10% water – also in the second applying.

- 1: At the first applying, the painting must be mixed with 10-20 % water
- 2: After 1-6 hours the second applying can be done

Technical Data:

Colour:	Black, anthracite grey, red-brown, grey, mocca, tile- red, Bordeaux
Dilute:	With water
Coverage:	On absorbent material app. 4-10 m ² per litre
Applications method:	Brushing, rolling or spraying
Applications temperature:	Min. 5 °C / max. 30 °C
Gloss:	App. 20 or 12
Dry matter content:	App. 50 w/w %
Drying time:	App. 1 hour at 20°C
Storage:	Dry, non-freezing, out of reach for children
Cleaning:	Tools in water



Adhesion DIN EN ISO 4624 - assessed as excellent

Flexibility DIN 53 504 - assessed as highly elastic, 197% flexible

Water vapour transmission rate (permeability) DIN EN ISO 7783-2 - assessed as excellent

Water repulsion DIN EN ISO 1062-3 - assessed as good

Gloss value and colour change - DIN EN ISO 4892-3, DIN 53 166 and DIN EN ISO 2810 - assessed as no changes in durability and little change in gloss value and colour

Tvaervej 6
6640 Lunderskov
Denmark
Tlf.: +45 7633 3114
Fax +45 7633 3115
E-mail: mail@isopaint.dk
www.isopaint.com



ISO PAINT NORDIC A/S