

# TG 80 Start Primer



## Product description



TG 80 Start Primer is used on asbestos cement and cement concrete tiles, before you apply the HB 80 Finish High Gloss roof coating. TG 80 Start Primer is available in the same colours as HB 80 Finish High Gloss roof coating.

## Use



Before application the roof must be cleaned very carefully. All dirt, alga, and moss must be taken away with A-cleaner. When the roof is clean and dry you apply TG 80 Start Primer. The best result will be achieved by spraying. After app. 1-2 hours, depending on temperature and RH, HB 80 Finish High Gloss roof coating can be applied.

**Please make a test coat of the surface for controlling the capability.**

## Technical data



**Colour:** Black, Bordeaux, mocca, tile red **Dilute:** If necessary with max. 5-15 % water **Coverage:** 4-8 m<sup>2</sup> per litre **Application method:** Brush, roller, or spray **Gloss:** App. gloss 10 **Dry matter content:** App. 55 w/w % **Drying time:** App. 1 hour at 20° C **Storage:** Dry, non-freezing, out of reach to children **Cleaning:** Tools are cleaned in water

## Benefits

**Perfect surface preparation for HB 80 Finish High Gloss Coating**



**Iso Paint Nordic A/S**  
Tvaervej 8  
6640 Lunderskov  
Denmark

Phone +45 7633 3114  
Fax +45 7633 3115

mail@isopaint.com  
www.isopaint.com



**DANAK**  
Quality &  
Environmental system  
according to  
DS/EN ISO 9001  
DS/EN ISO 14001  
by  
Det Norske Veritas,  
Danmark A/S  
Certification Dept.



ISO PAINT NORDIC A/S